

USPOREDNA TABLICA NEHRĐAJUĆIH ČELIKA

| STANDARD | | USA | NJEMAČKA | ITALIJA | FRANCUSKA | | ŠVEDSKA | VELIKA |
|--------------------|----------------|--------|-----------------------|--------------------|------------------|---------|---------|-----------|
| EN (EUROPA) | N ^o | AISI | DIN W. N ^o | UNI | AFNOR | JUS | SIS | BRITANIJA |
| | | | | | | | | BSI |
| X10 Cr-Ni 18-8 | 1.4310 | 301 | 1.4310 | X 12 Cr-Ni 1707 | Z 11 CN 18-08 | Č 4571 | 23 31 | 301 S 21 |
| | | 302 | 1.4319 | X 8 Cr-Ni 1910 | Z 12 CN 18-09 | | | 302 S 25 |
| X8 Cr-NiS 18-9 | 1.4305 | 303 | 1.4305 | X 10 Cr-NiS 1809 | Z 8 CNF 18-09 | Č 4590 | 23 46 | 303 S 21 |
| X5 Cr-Ni 18-10 | 1.4301 | 304 | 1.4301 | X 5 Cr-Ni 1810 | Z 7 CN 18-09 | Č 4580 | 23 32 | 304 S 15 |
| X2 Cr-NiN 18-10 | 1.4311 | 304 LN | 1.4311 | X 2 Cr-NiN 1811 | Z 3 CN 18-10 Az | Č 45707 | 23 71 | 304 S 61 |
| | | 304 H | | X 8 Cr-Ni 1910 | | | | |
| X2 Cr-Ni 18-9 | 1.4307 | 304 L | 1.4307 | | Z 3 CN 19-09 | | 23 52 | 304 S 11 |
| X2 Cr-Ni 19-11 | 1.4306 | 304 L | 1.4306 | X 2 Cr-Ni 1811 | Z 3 CN 18-10 | | 23 52 | 304 S 11 |
| X4 Cr-Ni 18-12 | 1.4303 | 305 | 1.4303 | X 8 Cr-Ni 1812 | Z 8 CN 18-12 | Č 45702 | 23 33 | 305 S 19 |
| X15 Cr-NiSi 20-12 | 1.4828 | 309 | 1.4828 | X 16 Cr-Ni 2314 | Z 17 CNS 20-12 | Č 4577 | | 309 S 24 |
| X12 Cr-Ni 23-13 | 1.4833 | 309 S | 1.4833 | X 6 Cr-Ni 2314 | Z 15 CN 23-13 | | | |
| | | 310 | 1.4845 | X 22 Cr-Ni 2520 | | | | 310 S 24 |
| X8 Cr-Ni 25-21 | 1.4845 | 310 S | 1.4845 | X 6 Cr-Ni 2520 | Z 8 CN 25-20 | | 23 61 | 310 S 16 |
| X15 Cr-NiSi 25-21 | 1.4841 | 314 | 1.4841 | X 16 Cr-NiSi 2520 | Z 15 CNS 25-20 | Č 4578 | | |
| X5 Cr-NiMo 17-12-2 | 1.4401 | 316 | 1.4401 | X 5 Cr-NiMo 1712 | Z 7 CND 17-11-02 | Č 4573 | 23 47 | 316 S 31 |
| X3 Cr-NiMo 17-13-3 | 1.4436 | 316 | 1.4436 | X 5 Cr-NiMo 1713 | Z 7 CND 17-12-02 | Č 45706 | 23 43 | 316 S 33 |
| | | 316 F | 1.4427 | | | | | |
| | | 316 N | | | | | | |
| | | 316 H | | X 8 Cr-NiMo 1712 | | | | |
| | | 316 H | | X 8 Cr-NiMo 1713 | | | | |
| X2 Cr-NiMo 17-12-2 | 1.4404 | 316L | 1.4404 | X 2 Cr-NiMo 1712 | Z 3 CND 17-11-02 | Č 45707 | 23 48 | 316 S 11 |
| X2 Cr-NiMo 18-14-3 | 1.4435 | 316L | 1.4435 | X 2 Cr-NiMo 1713 | Z 3 CND 18-14-03 | Č 45704 | 23 53 | 316 S 13 |
| X6 Cr-NiMo 17-12-2 | 1.4571 | 316Ti | 1.4571 | X 6 Cr-NiMoTi 1712 | Z 6 CNDT 17-12 | Č 4574 | 23 50 | 320 S 31 |
| X2 Cr-NiMo 18-15-4 | 1.4438 | 317L | 1.4438 | X 2 Cr-NiMo 1815 | Z 3 CND 19-15-04 | Č 45705 | 23 67 | 317 S 12 |
| X6 Cr-NiT 18-10 | 1.4541 | 321 | 1.4541 | X 6 Cr-NiT 1811 | Z 6 CNT 18-10 | Č 4572 | 23 37 | 321 S 31 |
| X10 Cr-NiT 18-10 | 1.4878 | 321H | 1.4878 | X 8 Cr-NiT 1811 | Z 6 CNT 18-10 | | 23 37 | 321 S 20 |
| X6 Cr-NiNb 18-10 | 1.4550 | 347 | 1.4550 | X 6 Cr-NiNb 1811 | Z 6 CNNB 18-10 | Č 4582 | 23 38 | 347 S 31 |
| X13 NiCr Si 35-16 | 1.4864 | 330 | 1.4864 | | Z 20 NCS 33-16 | Č 4579 | | |
| X3 Cr-NiMoN 27-5-2 | 1.4460 | 329 | 1.4460 | | Z 5 CND 27-05 Az | | 23 24 | |
| X6 CrAl 13 | 1.4002 | 405 | 1.4002 | X 6 CrAl 13 | Z 8 CA 12 | Č 49702 | | 405 S 17 |
| X2 Cr-Ti 12 | 1.4512 | 409 | 1.4512 | X 2 Cr-Ti 12 | Z 3 CT 12 | | | 409 S 19 |
| X6 Cr 13 | 1.4000 | 410S | 1.4000 | X 6 Cr 13 | Z 8 C 12 | Č 4170 | 23 01 | 403 S 17 |
| X6 Cr 17 | 1.4016 | 430 | 1.4016 | X 8 Cr 17 | Z 8 C 17 | Č 4174 | 23 20 | 430 S 17 |
| X6 CrMoS 17 | 1.4105 | 430F | 1.4105 | X 10 CrS 17 | Z 8 CF 17 | Č 47701 | | |
| X6 CrMo 17-1 | 1.4113 | 434 | 1.4113 | X 8 CrMo 17 | Z 8 CD 17-01 | | | 434 S 17 |
| X3 Cr-Ti 17 | 1.4510 | 439 | 1.4510 | X 6 Cr-Ti 17 | Z 4 CT 17 | Č 49701 | | |
| X18 CrN 28 | 1.4749 | 446 | 1.4749 | X 16 Cr 26 | | | 23 22 | |
| X12 Cr 13 | 1.4006 | 410 | 1.4006 | X 12 Cr 13 | Z 10 C 13 | Č 41701 | 23 02 | 410 S 21 |
| X12 CrS 13 | 1.4005 | 416 | 1.4005 | X 12 CrS 13 | Z 11 CF 13 | | 23 80 | 416 S 21 |
| X20 Cr 13 | 1.4021 | 420 | 1.4021 | X 20 Cr 13 | Z 20 C 13 | Č 4172 | 23 03 | 420 S 29 |
| X30 Cr 13 | 1.4028 | 420 | 1.4028 | X 30 Cr 13 | Z 33 C 13 | Č 4173 | 23 04 | 420 S 45 |
| X39 Cr 13 | 1.4031 | 420 | 1.4031 | | Z 33 C 13 | Č 41731 | 23 04 | 420 S 45 |
| X46 Cr 13 | 1.4034 | 420 | 1.4034 | X 40 Cr 14 | Z 44 C 14 | Č 4175 | | |
| X17 Cr-Ni 16-2 | 1.4057 | 431 | 1.4057 | X 16 Cr-Ni 16 | Z 15 CN 16-02 | Č 4570 | 23 21 | 431 S 29 |
| X70 CrMo 15 | 1.4109 | 440A | 1.4109 | | Z 70 C 15 | | | |
| X90 CrMoV 18 | 1.4112 | 440B | 1.4112 | | | Č 4772 | | |
| X105 CrMo 17 | 1.4125 | 440C | 1.4125 | | | | | |